

FLUORSID NORALF SYNTHETIC ANHYDRITE

1. CHEMICAL SPECIFICATION

CONTENT EXPRESSED AS	TYPICAL	MAX	METHODS OF ANALYSIS
CaSO ₄	95,5 - 98,5 %		By Difference
CaF ₂	0,5 – 3 %		Gravimetric
CaO	0,5 %	1%	Titration
pH	11 – 12,5		
H ₂ O (dry at 40° C)	< 0,1 %		

Analyses are carried out on representative samples of lot quantities.

2. PHYSICAL SPECIFICATION

Greyish white powder - suitable for self-levelling screeds, fillers, concrete mixtures, cement and fertilisers.

Bulk density: 1,2 - 1,3 kg/dm³

Particle size distribution	Typical
+ 5 mm	5 %
- 500 µm	60 %
- 150 µm	15 %
- 45 µm	2 %

3. PACKAGING

- Bulk shipment
- Bulk truck
- Big bag

Revised: 17.09.20